

Surface Composition 100% PVC

Base Composition 100% PS

| | | |
|---------------------------------------|----------------------------|--------------------------------|
| Tensile Strength EN ISO 421 | Warp 448 N 95% | Weft 334 N 157.1 % |
|---------------------------------------|----------------------------|--------------------------------|

Abrasion Test
EN ISO 5470-2 >800,000

Permanent Creasing Behavior (Bally Test) 200,00 cycles **PASS**
DIN EN ISO 32100/DIN 53359

| Color Fastness: | Dry | Wet |
|--|------------|------------|
| Rubbing EN ISO 105-X12 | 5 | 5 |
| Artificial Light EN ISO 105-B02 Exposure Level 7 | >7 | |
| Sea Water EN ISO 105-E02 | 5 | |
| Chlorine Water EN ISO 105-E03 | 5 | |
| Artificial Weathering EN ISO 105-B04 | >5 | |

APPLICATIONS & FEATURES

Durability Performance:
Abrasion Test >300,000 cycles (Heavy Use)

Resistance:
UV/Fading (QUV 1000h)
Hydrolysis (10 years)
Cold Cracking (-23°C)

Anti-Bacterial and Anti-Mildew | Impermeability | Chemical Solvents-Free | Respects the Environment

| | |
|---|-------------|
| Fire Proof Norms: | |
| BS 5852 Part 1 - Cigarette + Match Test | PASS |
| EN 1021-1/2 - Cigarette + Match Test | PASS |
| CA TB 117-2013 - Cigarette Test | PASS |
| NFPA 260-2013 | PASS |

CLEAN & CARE INSTRUCTIONS

Frequent washing may effect the performance of the article. Any stains, spills, or soiling should be cleaned up promptly with a neutral soap solution using a cloth in smooth circular motions. We do not accept responsibility for any damage resulting from inappropriate use or chemical cleaning.

